

Reynoplate® Engineering Properties

Technical Engineering Properties

Reynoplate® is a 3mm sheet of solid aluminum plate.

U.S. and Metric Equivalent

PROPERTY	Units	Reynoplate® 3mm Mill Finish Plate	Reynoplate® 3mm Coil Coated Plate
THICKNESS	in mm	0.118 3.0 (Nominal)	0.118 3.0 (Nominal)
THICKNESS TOLERANCE	in mm	+/- 0.007 0.18	+/- 0.007 0.18
AVAILABLE WIDTH	in mm	50, 62, 72 1270, 1575, 1829	50, 62 1270, 1575
WIDTH TOLERANCE	in mm	+/- 0.125 3.18	+/- 0.125 3.18
MAX. LENGTH	in mm	168 1700	168 1700
LENGTH TOLERANCE	in mm	-0, +0.25 -0, +6.35	-0, +0.25 -0, +6.35
WEIGHT	lb/ft ² kg/m ²	1.7 8.3	1.7 8.3
ALLOY AND TEMPER	N/A	3003 H16	3003 H16
ALLOWABLE BENDING STRESS	lb/in ² MPa	12,618 87	12,618 87
COEFF. OF EXPANSION	in/in/°F mm/mm/°C	1.28x10 ⁻⁵ 2.3x10 ⁻⁵	1.28x10 ⁻⁵ 2.3x10 ⁻⁵
YIELD STRENGTH	lb/in ² MPa	21,030 145	21,030 145
MOMENT OF INERTIA (I)	in ⁴ /in cm ⁴ /m	1.44x10 ⁻⁴ 5.9x10 ⁻³	1.44x10 ⁻⁴ 5.9x10 ⁻³
SECTION MODULUS	in ³ /in cm ³ /m	2.4x10 ⁻³ 0.039	2.4x10 ⁻³ 0.039
TENSILE YIELD	lb/in ² MPa	27,000 186	27,000 186
BENDING / FOLDING	N/A	Routed grooves should leave 0.032" (0.7mm) of material to achieve 90° folds. Un-routed material should maintain a minimum 2T inner bending radius.	
FINISH / PERFORMANCE	N/A	Mill Finish	Coil Coated with 2 or 3 coat PVDF meets AAMA 2605/2604
COMBUSTIBILITY PERFORMANCE	Passed	Non-Combustible ASTM E136	Non-Combustible / Class A ASTM E136 / ASTM E84

Information contained herein or related hereto is intended only for evaluation by technically skilled persons, with any use thereof to be at their independent discretion and risk. Such information is believed to be reliable, but AAP shall have no responsibility or liability for results obtained or damages resulting from such use. AAP grants no license under, and shall have no responsibility or liability for infringement of, any patent or other proprietary right. Nothing in this document should be construed as a warranty or guarantee by AAP, and the only applicable warranties will be those set forth in AAP's acknowledgment or in any printed warranty documents issued by AAP. The foregoing may be waived or modified only in writing by an AAP officer.

Disclaimer:

Laws and building and safety codes governing the design and use of AAP's products, and specifically aluminum composite materials and solid aluminum plate, vary widely. It is the responsibility of the Laws and building and safety codes governing the design and use of AAP's products, and specifically aluminum materials and solid aluminum plate, vary widely. It is the responsibility of the owner, the architect, the general contractor, the installer and the fabricator/transformer, consistent with their roles, to determine the appropriate materials for a project in strict conformity to all applicable national, regional and local building codes and regulations.